



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page no: 25

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 06/2025-2026 (Steel).
Name of Client : GE (Army) CMH, Dhaka.
Ref.ltr.No : CEA/418 of 2024-2025/07/E-6 Dt.25 Jun'2025.
Project Name : Construction of Multistoried Hospital Bldg.
Dt. of Sample Collection: 02 July'2025

Copy No : 05
Sample Specimen : Length 600mm , Dia 25mm
Sample Grade : 60
Frog Mark : RSM B-420 DWR.

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	(Fult/Fy)	8inch	5d	8inch	5d
1	0.984 25.00	0.989 25.11	0.7609 490.8739	2.613 3.888	2.613 3.888	60771.73 270.32	79873 551	79229 546	81047.75 360.52	106522 735	105267 726	1.33	25.5		26	
2	0.984 25.00	0.989 25.11	0.7609 490.8739	2.613 3.888		59529.49 264.80	78240 540		78480.00 349.09	103147 711		1.32	26			
3	0.984 25.00	0.989 25.11	0.7609 490.8739	2.613 3.888		60545.02 269.32	79575 549		80751.65 359.20	106133 732		1.33	27.5			

Cautions:

1. Samples as supplied to the laboratory have been tested.The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Ovservation on Specimen(if any):

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength N/mm2 or Mpa	Ult.Str N/mm2 or Mpa	Elongation %	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
										10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12	..	..
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

Laboratory Technician

Test Performed By

Vetted By