



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page no: 25

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 07/2025-2026 (Steel).

Copy No : 05

Name of Client : GE (Army) Sylhet.

Sample Specimen : Length 600mm , Dia 25mm

Ref.ltr.No : PDCAS/73 of 2024-2025/15/E-6 Dt.01 July'2025.

Sample Grade : 60

Project Name : Vertical Extension of Sena nir-1.

Frog Mark : AKS B-500 DWR.

Dt. of Sample Collection: 03 July'2025

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	(Fult/Fy)	8inch	5d	8inch	5d
1	0.984 25.00	0.975 24.76	0.7609 490.8739	2.540 3.779	2.540 3.779	67126.35 298.59	88225 608	89004 614	82977.04 369.10	109057 752	110083 759	1.24	26		26	
2	0.984 25.00	0.975 24.76	0.7609 490.8739	2.540 3.779		67341.48 299.55	88508 610		84105.93 374.12	110541 762		1.25	26.5			
3	0.984 25.00	0.975 24.76	0.7609 490.8739	2.540 3.779		68690.13 305.55	90280 623		84189.21 374.49	110651 763		1.23	24.5			

Cautions:

1. Samples as supplied to the laboratory have been tested.The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Ovservation on Specimen(if any):

1. Diameter & Unit weight of 25 mm bar is less than the standard value but within tolerance limit according to MES Schedule of Rates-2016.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E)				Minimum Standard Requirments(ASTM A615/A616M-96a)									
Grade				ASTM A 615 M		ASTM A 615 M		ASTM A 615/A 615 M					
				Y/strength	Ult.Str	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)					
				N/mm2 or Mpa	N/mm2 or Mpa	psi (kg/cm2)	psi (kg/cm2)	Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12	..	..	
400/400w	400	440	14	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6	

Laboratory Technician

Test Performed By

Vetted By