



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page no: 40

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 10/2025-2026 (Steel).
Name of Client : AGE (Army) Momenshahi.
Ref.ltr.No : CEA /262 of 2022-2023/35/E-6 Dt.08 July'2025.
Project Name : Construction of 1 x 660 SMBK
Dt. of Sample Collection: 09 July'2025

Copy No : 05
Sample Specimen : Length 600mm , Dia 25mm
Sample Grade : 60
Frog Mark : Baizid B-420 DWR.

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	(Fult/Fy)	8inch	5d	8inch	5d
1	0.984 25.00	0.999 25.39	0.7609 490.8739	2.670 3.973	2.670 3.973	55377.12 246.33	72783 502	73586 507	73427.76 326.62	96507 666	97103 670	1.33	25.5		24	
2	0.984 25.00	0.999 25.39	0.7609 490.8739	2.670 3.973		56598.54 251.76	74388 513		74128.69 329.74	97428 672		1.31	24.5			
3	0.984 25.00	0.999 25.39	0.7609 490.8739	2.670 3.973		55990.14 249.06	73588 508		74087.05 329.55	97373 672		1.32	23			

Cautions:

1. Samples as supplied to the laboratory have been tested.The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Ovservation on Specimen(if any):

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength N/mm2 or Mpa	Ult.Str N/mm2 or Mpa	Elongation %	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
										10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12	..	..
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

Laboratory Technician

Test Performed By

Vetted By