



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page no: 50

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 12/2025-2026 (Steel).
Name of Client : GE (Air) Chattogram.
Ref.ltr.No : CEA (Air)/235 of 2024-2025/08/E-6 Dt.14 July'2025.
Project Name : Repair/Maint works of Bldg No: 205 Raised platform.
Dt. of Sample Collection: 15 July'2025

Copy No : 05
Sample Specimen : Length 600mm , Dia 25mm
Sample Grade : 72.50
Frog Mark : GPH B-500 DWR.

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	(Fult/Fy)	8inch	5d	8inch	5d
1	0.984 25.00	0.981 24.91	0.7609 490.8739	2.572 3.827	2.572 3.827	68690.13 305.55	90280 623	90512 624	85759.94 381.48	112715 777	113004 779	1.25	24		21	
2	0.984 25.00	0.981 24.91	0.7609 490.8739	2.572 3.827		68912.21 306.54	90572 625		86079.17 382.90	113135 780		1.25	19			
3	0.984 25.00	0.981 24.91	0.7609 490.8739	2.572 3.827		68997.80 306.92	90684 625		86099.99 382.99	113162 780		1.25	21			

Cautions:

1. Samples as supplied to the laboratory have been tested.The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecured and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Ovservation on Specimen(if any):

1. Diameter & Unit weight of 25 mm bar is less than the standard value but within tolerance limit according to MES Schedule of Rates-2016.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M		ASTM A 615 M			ASTM A 615/A 615 M				
Grade	Y/strength N/mm2 or Mpa	Ult.Str N/mm2 or Mpa	Elongation %	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
										10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12	..	..
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

Laboratory Technician

Test Performed By

Vetted By