



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No : 490

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 364/2024-2025 (Con).

Name of Client : GE (Army) Ghatail.

Ref ltr no : CEA/569 of 2021-2022/66/E-6 Dt.17 Dec' 2024.

Name of the project : Construction of Garrison mosque.

Status of sample : Foundation.

Dt of sample collection: 19 Dec'2024

Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Type of Aggregate : Stone

Brand &Type of Cement : Shah Opc.

Proportion of Mixture : 1:1.5:3

Desired Design Strength : 2275 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	12 Dec'2024 (07 days)	19 Dec'2024	12.17	47462.62	3900	Average of Sample 1, 2 & 3 4019	Combined Failure
2			12.17	49225.08	4045		
3			12.17	50038.53	4112		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By