



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No: 566

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 367/2024-2025 (Con).
Name of Client : GE (Army) Mirpur.
Ref ltr no : EinC/320 of 2022-2023/258/E-4 Dt.18 Dec'2024.
Name of the project : Construction of 1 x 150 Officer's Mess & 1 x 450 BOQ.
Status of sample : Foundation.
Dt of sample collection: 19 Dec'2024
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand &Type of Cement : Seven Ring Opc.
Proportion of Mixture : 1:1.5:3
Desired Design Strength : 3600 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	15 Dec'2024 (28 days)	12 Jan'2025	12.17	52365.23	4303	Average of Sample 1, 2 & 3 4350	Combined Failure
2			12.17	51089.43	4198		
3			12.17	55372.49	4550		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By