



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No: 655

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 489/2024-2025 (Con).
Name of Client : AGE (Air) Shamsheernagar.
Ref ltr no : EinC/166 of 2023-2024/31/E-6 Dt.12 Feb'2025.
Name of the project : Construction of 1 x Office cum Laboratory Building.
Status of sample : Column, wall, beam, stair & Landing etc (Ground floor).
Dt of sample collection: 16 Feb'2025
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand & Type of Cement : Seven rings Opc.
Proportion of Mixture : 1:1.5:3
Desired Design Strength : 2356 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	10 Feb'2025 (07 days)	17 Feb'2025	12.17	37465.64	3079	Average of Sample 1, 2 & 3 2833	Combined Failure
2			12.17	33569.88	2758		
3			12.17	32407.98	2663		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]