



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICES(MES)**

Page No: 711

Copy no : 02

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 493/2024-2025 (Con).  
Name of Client : GE (Army) Central, Dhaka.  
Ref ltr no : EinC/91 of 2022-2023/135/E-6 Dt.17 Feb'2025.  
Name of the project : Construction of 26 x JCO's Qtr and 52 x OR's Qtr.  
Status of sample : 10th floor Roof .  
Dt of sample collection: 17 Feb'2025  
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")  
Type of Aggregate : Stone  
Brand & Type of Cement : Shah Opc.  
Proportion of Mixture : Not Mentioned.  
Desired Design Strength : 4000 Psi.

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	10 Feb'2025 (28 days)	10 Mar'2025	12.17	70741.92	5813	Average of Sample 2 & 3  4522	Combined Failure
2			12.17	56067.91	4607		
3			12.17	53990.76	4436		

**Cautions :**

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm2=14.223 Psi]