



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICE(MES)

Page No : 739

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 542/2024-2025 (Con).

Name of Client : GE (Army) Sylhet.

Ref ltr no : CEA/611 of 2022-2023/19/E-6 Dt.12 Mar' 2025.

Name of the project : Construction of 300 Bedded Combined Military Hospital (CMH).

Status of sample : 2nd floor column & roof beam.

Dt of sample collection: 13 Mar'2025

Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Type of Aggregate : Stone

Brand &Type of Cement : Seven rings Opc.

Proportion of Mixture : 1:1.25:2.5

Desired Design Strength : 2600 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	10 Mar'2025 (07 days)	17 Mar'2025	12.17	35542.16	2920	Average of Sample 1 & 2 2930	Combined Failure
2			12.17	35765.51	2939		
3			12.17	25245.78	2074		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]