



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICES(MES)**

Page No: 820

Copy no : 01

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 600/2024-2025 (Con).  
Name of Client : AGE (Army) Jahanabad.  
Ref ltr no : 6000/Test/103/E-6 Dt.23 Apr'2025.  
Name of the project : Construction of 1 x 50 Bedded CMH.  
Status of sample : 1st floor Column.  
Dt of sample collection: 24 Apr'2025  
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")  
Type of Aggregate : Stone  
Brand & Type of Cement : Elephant Opc.  
Proportion of Mixture : 1:1.5:3  
Desired Design Strength : 2600 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	17 Apr'2025 (07 days)	24 Apr'2025	12.17	37485.29	3080	Average of Sample1, 2 & 3  2969	Combined Failure
2			12.17	34626.43	2845		
3			12.17	36301.54	2983		

**Cautions :**

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]