



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No: 865

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 601/2024-2025 (Con).
Name of Client : AGE (Air) Shamshernagar.
Ref ltr no : CE Air/92 of 2024-2025/10/E-6 Dt.18 Apr'2025.
Name of the project : Construction of Ground & 1st floor of under Construction Airmen BK.
Status of sample : Roof, slabs, sunshade & shelves etc (1st floor).
Dt of sample collection: 24 Apr'2025
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand & Type of Cement : Seven rings Opc.
Proportion of Mixture : 1:1.5:3
Desired Design Strength : 3600 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	18 Apr'2025 (28 days)	16 May'2025	12.17	48094.36	3952	Average of Sample 2 & 3 4642	Combined Failure
2			12.17	59485.14	4888		
3			12.17	53499.40	4396		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]