



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No : 843

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 616/2024-2025 (Con).
Name of Client : GE (Navy) Khulna.
Ref ltr no : EinC/58 of 2024-2025/05/E-6 Dt.07 May'2025.
Name of the project : Provision of Causeway Connecting Road.
Status of sample : Foundation.
Dt of sample collection: 08 May'2025
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand & Type of Cement : Premier Opc.
Proportion of Mixture : 1:1.5:3
Desired Design Strength : 2275 Psi.

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	01 May'2025 (07 days)	08 May'2025	12.17	30695.49	2522	Average of Sample 1, 2 & 3 2617	Combined Failure
2			12.17	31946.24	2625		
3			12.17	32906.64	2704		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]