



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No : 960

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 682/2024-2025 (Con).
Name of Client : GE (Air) Jashore.
Ref ltr no : CE Air/116 of 2021-2022/53/E-6 Dt.23 Jun'2025.
Name of the project : Construction of catering flight including store room.
Status of sample : Ground Floor beam & Slab.
Dt of sample collection: 24 Jun'2025
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Brick
Brand &Type of Cement : Seven ring's Opc.
Proportion of Mixture : 1:2:4
Desired Design Strength : 1625 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	18 Jun'2025 (07 days)	25 Jun'2025	12.17	37775.64	3104	Average of Sample 1, 2 & 3 3126	Combined Failure
2			12.17	40746.29	3348		
3			12.17	35597.50	2925		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]