

#### MATERIAL TESTING LABORATORY Page No: 93 **MILITARY ENGINEER SERVICES (MES)** Copy no: 01 TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Job No : 72/2024-2025 (Sand). Name of Clint : GE (Navy) Khulna.

Ref Itr no : EinC/18 of 2023-2024/20/E-6 Dt.27 Apr'2025 Project Name : Construction of 260 Meter Multipurpose Jetty.

: Sylhet Sand. Sample Specimen Dt of sample collection: 28 Apr'2025

Test Standard: ASTM/BS

Sieve Size	Wt of Material	Percentage Matarial	Cumulative % Retained	%Finer	Remarks
	Retained(gms)	Retained(Round)			
# 4	1.44	0.36	0.36		
# 8	15.48	3.87	4.23		
#16	68.95	17.24	21.47		
# 30	214.32	53.58	75.05		
# 50	91.18	22.80	97.84		FM= 2.99
#100	7.85	1.96	99.81		
# 200	0.44	0.11			
#Pan	0.18	0.05			
			Σ= 298.75		

# Cautions:

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- In oder to be avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

# Observation on Specimen(if any):

Laboratory Technician Test Performed By Vetted By

### Permissable Value:

1.For Sylhet/Domar sand minimum FM will be = 2.50

2.For Local sand minimum FM will be = 1.5

3.For Vitty sand minimum FM will be = 0.80



# MATERIAL TESTING LABORATORY Page No: 93 MILITARY ENGINEER SERVICES (MES) Copy no: 02 TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Job No : 72/2024-2025(Sand).
Name of Clint : GE (Navy) Khulna.

Ref ltr no : EinC/18 of 2023-2024/20/E-6 Dt.27 Apr'2025
Project Name : Construction of 260 Meter Multipurpose Jetty.

Sample Specimen : Local Sand Dt of sample collection : 28 Apr'2025

Test Standard: ASTM/BS

Sieve Size	Wt of Material	Percentage Matarial	Cumulative % Retained	%Finer	Remarks
	Retained(gms)	Retained(Round)			
# 4	0	0.00	0.00		
# 8	10.17	2.54	2.54		
#16	25.73	6.43	8.98		
# 30	32.18	8.05	17.02		
# 50	115.24	28.81	45.83		FM= 1.68
#100	193.04	48.26	94.09		
# 200	19.96	4.99			
#Pan	3.68	0.92			
			Σ= 168.46		

### Cautions:

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- In oder to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

# Observation on Specimen(if any):

1

<u>Laboratory Technician</u> <u>Test Performed By</u> <u>Vetted By</u>

### Permissable Value:

1.For Sylhet/Domar sand minimum FM will be = 2.50

2.For Local sand minimum FM will be = 1.5

3.For Vitty sand minimum FM will be = 0.80