



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)
TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Page No: 104

Copy no : 02

Job No : 85/2024-2025(Sand).
Name of Clint : GE (Army) Rangpur.
Ref ltr no : EinC/110 of 2024-2025/07/E-6 Dt.14 May'2025
Project Name : Construction of Drain & Box Culvert.
Sample Specimen : Sylhet Sand
Dt of sample collection :17 May'2025
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retained(gms)	Percentage Material Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	0.00	0.00	0.00		
# 8	23.45	5.86	5.86		
#16	145.51	36.38	42.24		
# 30	163.32	40.83	83.07		
# 50	59.02	14.76	97.83		FM= 3.29
#100	8.43	2.11	99.93		
# 200	0.03	0.01	...		
#Pan	0.17	0.04	...		
			Σ= 328.93		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80