



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)
TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Page No: 107

Copy no : 02

Job No : 89/2024-2025(Sand).
Name of Clint : GE (Army) Rangpur.
Ref ltr no : EinC/109 of 2024-2025/08/E-6 Dt.14 May'2025
Project Name : Construction of 1x Mosque .
Sample Specimen Sylhet Sand
Dt of sample collection :17 May'2025
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retained(gms)	Percentage Material Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	1.71	0.43	0.43		
# 8	25.62	6.41	6.83		
#16	64.82	16.21	23.04		
# 30	164.21	41.05	64.09		
# 50	121.31	30.33	94.42		FM= 2.88
#100	19.29	4.82	99.24		
# 200	2.38	0.60	..		
#Pan	0.53	0.13	...		
			Σ= 288.05		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80